



JAZA MINERALS

A Name of Quality

Typical Analysis Fluorite

CaF₂ 89-90

Test Item Parameter	Test Method Protocol	Unit	Test result
Calcium Fluoride (CaF ₂)	Based on ASTM E-815 17	%	90
Soluble Calcium Carbonate (CaCO ₃)		%	02.57
Silica as SiO ₂	Based on ASTM E 1506-08	%	05.27
Sulphur (S)	Fusion Method Final Finished on ICP-OES	%	00.07
Phosphorus (P)	Fusion Method Final Finished on ICP-OES	%	00.03
Moisture	Gravimetric	%	00.07

Note:

Sizes can be altered on clients request



HEAD OFFICE

+92-321-8790952
haris.abdullah@jazaminerals.com
info@jazaminerals.com
www.jazaminerals.com
abdullah_09049
Plot No. R-209, Sector 8, North Karachi (71500)

FACTORY ADDRESS

Plot 49, NA Class No.1, Deh Moach,
Karachi, Karachi West Baldia Town
75760

